

၁၉။ သတ္တုရိုင်းနမူနာ (Selected Sample) ၁၇ ခု၏ XRF ဓာတ်ခွဲအဖြေအရ Oxide Form ပါဝင်မှုအား အောက်ပါအတိုင်းတွေ့ရှိရပါသည်-

		PbO %	BaO %	TiO <sub>2</sub> %	V <sub>2</sub> O <sub>5</sub> %	ZrO <sub>2</sub> %	SiO <sub>2</sub> %	SO <sub>3</sub> %
Samples	Valid	14	17	12	15	8	14	16
	Missing	3	0	5	2	9	3	1
Average		11.05671	24.6100	16.1258	2.93920	3.0350	9.4486	31.94988
Minimum		.247	2.07	4.97	.874	1.96	2.47	.908
Maximum		38.800	51.80	32.90	6.640	4.79	22.30	66.300

		Al <sub>2</sub> O <sub>3</sub> %	Ag <sub>2</sub> O %	CuO %	Fe <sub>2</sub> O <sub>3</sub> %	CaO %	SrO %	MgO %
Samples	Valid	7	3	1	3	4	7	1
	Missing	10	14	16	14	13	10	16
Average		2.8929	.059733	0.3040 0	2.6367	19.438 25	1.1929	10.100
Minimum		1.14	.0493	0.304	1.95	.453	.26	10.1
Maximum		7.17	.0665	0.304	3.57	51.200	2.39	10.1

		K <sub>2</sub> O %	HgO %	Na <sub>2</sub> O %	MnO %	Sc <sub>2</sub> O <sub>3</sub> %
Samples	Valid	2	2	2	1	5
	Missing	15	15	15	16	12
Average		5.1100	.057850	5.4400	.26800	.247020
Minimum		.12	.0310	4.74	.268	.0861
Maximum		10.10	.0847	6.14	.268	.3950

		Nd <sub>2</sub> O <sub>3</sub> %	Eu <sub>2</sub> O <sub>3</sub> %	Tb <sub>4</sub> O <sub>7</sub> %	Sm <sub>2</sub> O <sub>3</sub> %	Y <sub>2</sub> O <sub>3</sub> %
Samples	Valid	10	10	2	3	1
	Missing	7	7	15	14	16
Average		.59610	.72430	.73150	.46100	.058800
Minimum		.258	.191	.123	.340	.0588
Maximum		.900	1.280	1.340	.669	.0588

